

BENGglas® Double Coated



BENG||GLAS



DOUBLE LOW E
COATING POS 2

CONSTRUCTIE | COMPOSITION | KONSTRUKTION | CONSTRUCTION

Buitenblad	
Exterieur	4T
Außen	
Outer pane	
Verdeler	0,3 Vacuüm
SZR	0,3 Vakuum
Intercalaire	0,3 Sous-vide
Spacer	0,3 vacuum
Binnenblad	
Intérieur	4T
Innen	
Inner Pane	

SPECIFICATIES | SPÉCIFICATIONS | SPEZIFIKATIONEN | SPECIFICATIONS

LTA TL LT LT	70	Lichttransmissie Transmission Lumineuse Lichttransmission Light transmission
BLR RLE Lra ELR	11	Buiten lichtreflectie Réflexion Lumineuse Extérieure Lichtreflexion außen External light reflection
LR (binnen) RLI Lri ILR	12	Binnen lichtreflectie Réflexion lumineuse Intérieure Lichtreflexion innen Internal light reflection
G-waarde Valeur G G-wert G-value	0,39	Zontoetredingsfactor Facteur Solaire Gesamtenergiedurchlassgrad Solar factor
EN674 U-waarde Valeur U U-Wert U-value	0,40*	Isolatiewaarde Valeur d'isolation Dämmwert Insulation value
EN ISO 10140-1 / 2 RW (C ; Ctr) dB EN ISO 717-1	36 (-2;-3)	Geluidsdemping Réduction du bruit Lärmminderung Sound insulation

*U-waarde gebaseerd op EN 674:2011 en ISO 19916-1:2018 (ift rosenheim, 2025).

* Valeur U basée sur EN 674:2011 et ISO 19916-1:2018 (ift Rosenheim, 2025).

*U-value based on EN 674:2011 and ISO 19916-1:2018 (ift Rosenheim, 2025).

* U-Wert basierend auf EN 674:2011 und ISO 19916-1:2018 (ift Rosenheim, 2025).



Netherlands

www.bengglas.nl
info@bengproducts.nl
+31 (0) 13 534 22 26

Belgium

www.bengglas.be
info@bengproducts.be
+32 (0) 19 60 08 31

